



Bona Mega

ONE COMPONENT, WATERBORNE COATING

Simplicity for medium commercial and heavy domestic wood floors

TECHNICAL DATA

Product type:	1-component oil-modified polyurethane topcoat.
Solids content:	approx. 32%
Sheen (at 60°):	Gloss 90%, Silk matt 50%, Matt 25%, Extra Matt 9% (on glass).
Dilution:	If required, dilute with 4% Bona Retarder for a longer open time.
Drying time, until:	Recoating: 2 - 3 hours* Light use: 8 hours* Possible to cover: 7 days* *under normal climate conditions, 20° C / 60% R.H.
Application tools:	Bona Roller or Bona Swivel Head Bar Applicator.
Application rate:	8 - 10 m ² / L per coat
Safety	Unclassified
Cleaning:	Wipe tools free from residual material. Clean with a minimum of water. Remove dried material with acetone.
Shelf life:	1 year from date of production in unopened original container.
Storage/transport:	The temperature must not fall below +5° C or exceed +30° C during storage and transport.
Disposal:	Waste and emptied containers should be handled in accordance with local regulations.
Pack size	5 litres
Certificates:	EMICODE EC2 low emission GREENGUARD EN 13501-1; Reaction to fire EN 71-3: Application on children's toys

Additional detailed information is noted in the appropriate Safety Data Sheet.

PREPARATION

Ensure the floor is acclimatised to its end-use environment. The surface must be sanded back to bare wood, dry and free from sanding dust, oil, wax and other contamination. The wood surface should be coated with a Bona primer prior to the application of Bona Mega.

Allow the lacquer to reach room temperature, insert filter and shake the container thoroughly before use. Optimal conditions for use are between 18 - 25° C and 30 - 60% relative air humidity. High temperatures and low humidity shorten drying times, low temperatures and high humidity lengthen drying times.

Minimum temperature for use is 13° C.



Bona Mega

ONE COMPONENT, WATERBORNE COATING

Simplicity for medium commercial and heavy domestic wood floors

TREATMENT SCHEDULE

Standard protocol untreated wood:

- 1 x Bona Primer
- 1 x Bona Mega
- Light sanding 150 grit
- 1 x Bona Mega

Bona Mega has a subtle rich tone which is more noticeable when used over light wood species and on floors treated with a light or pastel stain. It is also not recommended therefore to overcoat Bona White primer with Bona Mega if you are looking to achieve a true white look.

Observe: It is not recommended to apply more than two full coats of primer and/or lacquer per day due to risk of excessive wood swelling. Ensure good ventilation during drying. Poor drying conditions may reduce product performance and adhesion.

APPLICATION

- 1) Shake the lacquer thoroughly for one minute.
- 2) Apply using a Bona Roller at 8 - 10 m² / L. Roll alternately across and with the grain of the wood avoiding accumulations of product. Always maintain a "wet edge" to avoid overlaps.
- 3) Allow to dry properly before applying further layers. Ensure proper ventilation.
- 4) If necessary, make an intermediate sanding using the Bona Scrad System P150 grit (or finer) and remove dust before applying a final layer of lacquer. **Note:** If the previous layer of lacquer / primer has been allowed more than 24 hours drying time then an intermediate sanding is always required.

Light foot traffic can be resumed after 8 hours but the surface remains susceptible to scratching and marring until fully cured. Full cure is achieved after approximately seven days. Do not cover or damp mop the surface during this time

MAINTENANCE

Cleaning with the correct products is easy. When you choose Bona cleaning and maintenance products you can relax knowing that you have chosen the best possible product to help you care for your floor.

End user maintenance instructions are available on bona.com.au. Detailed maintenance instructions are available for both homeowners and professional end users. **Please print out a copy of the relevant instructions and give it to the end user.**



Bona Mega

ONE COMPONENT, WATERBORNE COATING

Simplicity for medium commercial and heavy domestic wood floors

IMPORTANT!

- Plasticisers found in materials such as carpet underlays, furniture legs, castors and adhesives can lead to softening and discolouration. Exposure to hair dyes or rubber tyres on cycles, baby strollers, etc. can lead to permanent, irreversible discolouration of the surface. Use protection or completely avoid contact.
- Spills should be removed promptly. Unattended spills may cause cosmetic stains or damage the surface. Please note that whilst Bona lacquers are designed to provide a sealed surface that is resistant to wear, scuffing and spillage, etc. no surface applied finish system can prevent physical damage to the timber or “harden” the floor. Indentations in the wood and scratches may be caused by furniture, dropped items, dog claws, etc. and steps should be taken to reduce the possibility of this occurring.

The information in this document and all other advice and recommendations that we provide to help and assist the applicator are based on previous experience and extensive testing but makes no claim to be complete. Because of the wide range of possible uses and conditions of application of our products, we do not relieve users from the need to carry out their own trials or to seek technical advice from Bona before use. Bona can only guarantee its products and not the construction as a whole. Observe recommendations from flooring manufacturer and the provisions of relevant standards.

2025-03-2025

This data sheet replaces all previous versions
please check bona.com.com to ensure that you
have the latest version